

NOVAGUARD™ 260

DESCRIPTION

<https://www.verfschilderen.nl/sigma-guard-260-set.html>

Two-component, high-build, amine adduct-cured novolac phenolic epoxy primer/coating

PRINCIPAL CHARACTERISTICS

- Tank coating with excellent resistance to alcohols, fats, solvents and various other chemicals*
- Can be used as holding primer for all solvent-free epoxy and novolac tank coatings
- Can be used for hot water and hot oil storage up to 90°C (195°F)
- Good application properties, resulting in a smooth easy cleanable surface
- Can be applied and cures at temperatures down to 5°C (41°F)
- Good abrasion resistance

Note: * See the full Chemical Resistance List for more detailed information

COLOR AND GLOSS LEVEL

- Pink (gray on request)
- Eggshell

BASIC DATA AT 20°C (68°F)

Data for mixed product	
Number of components	Two
Mass density	1.7 kg/l (14.2 lb/US gal)
Volume solids	68 ± 2%
VOC (Supplied)	Directive 1999/13/EC, SED: max. 194.0 g/kg max. 328.0 g/l (approx. 2.7 lb/US gal)
Recommended dry film thickness	50 - 150 µm (2.0 - 6.0 mils)
Theoretical spreading rate	13.7 m²/l for 50 µm (545 ft²/US gal for 2.0 mils) 4.5 m²/l for 150 µm (182 ft²/US gal for 6.0 mils)
Dry to touch	3 hours
Overcoating Interval	Minimum: 8 hours Maximum: 1 month
Full cure after	See curing table
Shelf life	Base: at least 12 months when stored cool and dry Hardener: at least 12 months when stored cool and dry

Notes:

- See ADDITIONAL DATA – Spreading rate and film thickness
- See ADDITIONAL DATA – Overcoating intervals
- See ADDITIONAL DATA – Curing time

NOVAGUARD™ 260

RECOMMENDED SUBSTRATE CONDITIONS AND TEMPERATURES

Substrate conditions

- Steel; blast cleaned to a minimum of ISO-Sa2½
- Blasting profile 50 – 100 µm (2.0 – 4.0 mils)
- The substrate must be perfectly dry before and during application of NOVAGUARD 260

Substrate temperature and application conditions

- Substrate temperature during application and curing should be above 5°C (41°F)
- Substrate temperature during application should be at least 3°C (5°F) above dew point

SYSTEM SPECIFICATION

For use as a holding primer

- NOVAGUARD 260: 50 to 75 µm (2 to 3 mils)

For use as a tank coating

- NOVAGUARD 260: 2 x 125 to 150 µm (5 to 6 mils)

INSTRUCTIONS FOR USE

Mixing ratio by volume: base to hardener 87:13

- The temperature of the mixed base and hardener should preferably be above 15°C (59°F), otherwise extra thinner may be required to obtain application viscosity
- Adding too much thinner results in reduced sag resistance and slower cure
- Thinner should be added after mixing the components

Induction time

Allow induction time before use

Mixed product induction time	
Mixed product temperature	Induction time
5°C (41°F)	20 minutes
10°C (50°F)	15 minutes
15°C (59°F)	10 minutes

Pot life

2 hours at 20°C (68°F)

Note: See ADDITIONAL DATA – Pot life

NOVAGUARD™ 260

Air spray

Recommended thinner

THINNER 91-92

Volume of thinner

5 - 10%, depending on required thickness and application conditions

Nozzle orifice

2.0 mm (approx. 0.079 in)

Nozzle pressure

0.3 MPa (approx. 3 Bar; 44 p.s.i.)

Airless spray

Recommended thinner

THINNER 91-92

Volume of thinner

5 - 10%, depending on required thickness and application conditions

Nozzle orifice

Approx. 0.48 – 0.53 mm (0.019 – 0.021 in)

Nozzle pressure

15.0 MPa (approx. 150 bar; 2176 p.s.i.)

Brush/roller

- Only for touch-up and spot repair

Recommended thinner

THINNER 91-92

Volume of thinner

0 – 5%

Cleaning solvent

THINNER 90-53

NOVAGUARD™ 260

ADDITIONAL DATA

Spreading rate and film thickness	
DFT	Theoretical spreading rate
50 µm (2.0 mils)	13.6 m ² /l (545 ft ² /US gal)
75 µm (3.0 mils)	9.1 m ² /l (364 ft ² /US gal)
100 µm (4.0 mils)	6.8 m ² /l (273 ft ² /US gal)
150 µm (6.0 mils)	4.5 m ² /l (182 ft ² /US gal)

Note: Maximum DFT when brushing: 60 µm (2.4 mils)

Overcoating interval for DFT up to 100 µm (4.0 mils)							
Overcoating with...	Interval	5°C (41°F)	10°C (50°F)	15°C (59°F)	20°C (68°F)	30°C (86°F)	40°C (104°F)
itself, solvent-free epoxy and novolac tank coatings	Minimum	24 hours	20 hours	14 hours	8 hours	5 hours	3 hours
	Maximum	2 months	2 months	2 months	1 month	1 month	1 month

Note: Surface should be dry and free from any contamination

Overcoating interval for DFT up to 150 µm (6.0 mils)							
Overcoating with...	Interval	5°C (41°F)	10°C (50°F)	15°C (59°F)	20°C (68°F)	30°C (86°F)	40°C (104°F)
itself	Minimum	30 hours	24 hours	18 hours	10 hours	6 hours	4 hours
	Maximum	2 months	2 months	2 months	1 month	1 month	1 month

Curing time for DFT up to 75 µm (3.0 mils)		
Substrate temperature	Dry to handle	Full cure
5°C (41°F)	20 hours	10 days
10°C (50°F)	10 hours	7 days
20°C (68°F)	3 hours	5 days
40°C (104°F)	1 hour	3 days

Notes:

- Adequate ventilation must be maintained during application and curing (please refer to INFORMATION SHEETS 1433 and 1434)
- When used as a primer under solvent-free tank-linings the DFT must be limited to a maximum of 100 µm (4.0 mils)

NOVAGUARD™ 260

Pot life (at application viscosity)

Mixed product temperature	Pot life
5°C (41°F)	8 hours
10°C (50°F)	6 hours
15°C (59°F)	4 hours
20°C (68°F)	2 hours
40°C (104°F)	30 minutes

SAFETY PRECAUTIONS

- For paint and recommended thinners see INFORMATION SHEETS 1430, 1431 and relevant Material Safety Data Sheets
- This is a solvent-borne paint and care should be taken to avoid inhalation of spray mist or vapor, as well as contact between the wet paint and exposed skin or eyes

WORLDWIDE AVAILABILITY

It is always the aim of PPG Protective and Marine Coatings to supply the same product on a worldwide basis. However, slight modification of the product is sometimes necessary to comply with local or national rules/circumstances. Under these circumstances an alternative product data sheet is used.

REFERENCES

• CONVERSION TABLES	INFORMATION SHEET	1410
• EXPLANATION TO PRODUCT DATA SHEETS	INFORMATION SHEET	1411
• SAFETY INDICATIONS	INFORMATION SHEET	1430
• SAFETY IN CONFINED SPACES AND HEALTH SAFETY, EXPLOSION HAZARD – TOXIC HAZARD	INFORMATION SHEET	1431
• SAFE WORKING IN CONFINED SPACES	INFORMATION SHEET	1433
• DIRECTIVES FOR VENTILATION PRACTICE	INFORMATION SHEET	1434
• CLEANING OF STEEL AND REMOVAL OF RUST	INFORMATION SHEET	1490
• SPECIFICATION FOR MINERAL ABRASIVES	INFORMATION SHEET	1491
• RELATIVE HUMIDITY – SUBSTRATE TEMPERATURE – AIR TEMPERATURE	INFORMATION SHEET	1650

WARRANTY

PPG warrants (i) its title to the product, (ii) that the quality of the product conforms to PPG's specifications for such product in effect at the time of manufacture and (iii) that the product shall be delivered free of the rightful claim of any third person for infringement of any U.S. patent covering the product. THESE ARE THE ONLY WARRANTIES THAT PPG MAKES AND ALL OTHER EXPRESS OR IMPLIED WARRANTIES, UNDER STATUTE OR ARISING OTHERWISE IN LAW, FROM A COURSE OF DEALING OR USAGE OF TRADE, INCLUDING WITHOUT LIMITATION, ANY OTHER WARRANTY OF FITNESS FOR A PARTICULAR PURPOSE OR USE, ARE DISCLAIMED BY PPG. Any claim under this warranty must be made by Buyer to PPG in writing within five (5) days of Buyer's discovery of the claimed defect, but in no event later than the expiration of the applicable shelf life of the product, or one year from the date of the delivery of the product to the Buyer, whichever is earlier. Buyer's failure to notify PPG of such non-conformance as required herein shall bar Buyer from recovery under this warranty.



NOVAGUARD™ 260

LIMITATIONS OF LIABILITY

IN NO EVENT WILL PPG BE LIABLE UNDER ANY THEORY OF RECOVERY (WHETHER BASED ON NEGLIGENCE OF ANY KIND, STRICT LIABILITY OR TORT) FOR ANY INDIRECT, SPECIAL, INCIDENTAL, OR CONSEQUENTIAL DAMAGES IN ANY WAY RELATED TO, ARISING FROM, OR RESULTING FROM ANY USE MADE OF THE PRODUCT. The information in this sheet is intended for guidance only and is based upon laboratory tests that PPG believes to be reliable. PPG may modify the information contained herein at any time as a result of practical experience and continuous product development. All recommendations or suggestions relating to the use of the PPG product, whether in technical documentation, or in response to a specific inquiry, or otherwise, are based on data, which to the best of PPG's knowledge, is reliable. The product and related information is designed for users having the requisite knowledge and industrial skills in the industry and it is the end-user's responsibility to determine the suitability of the product for its own particular use and it shall be deemed that Buyer has done so, as its sole discretion and risk. PPG has no control over either the quality or condition of the substrate, or the many factors affecting the use and application of the product. Therefore, PPG does not accept any liability arising from any loss, injury or damage resulting from such use or the contents of this information (unless there are written agreements stating otherwise). Variations in the application environment, changes in procedures of use, or extrapolation of data may cause unsatisfactory results. This sheet supersedes all previous versions and it is the Buyer's responsibility to ensure that this information is current prior to using the product. Current sheets for all PPG Protective & Marine Coatings Products are maintained at www.ppgpmc.com. The English text of this sheet shall prevail over any translation thereof.

The PPG logo, and all other PPG marks are property of the PPG group of companies. All other third-party marks are property of their respective owners.

