



YachtCoatings

DELTA 3000

TECHNICAL DATA SHEET

Product description

Epoxy primer that provides an excellent adhesion on every duly treated surface. It can be covered with both epoxy fillers and with high thickness two-component undercoats. It is recommended as primer for parts of the vessel above and below the waterline.

Product information

Finish	Semi-matt		
Colour	White .001, Red .171		
Solids (by volume)	ASTM D2369		48± 2%
Specific gravity	UNI EN ISO 2811-1		1,50 ± 2 g/cm ³
Flash point	UNI EN ISO 13736		30 °C
VOC (calculated average content)	ISO 11890-2/2006		447 g/l
Packaging	0,75 – 2,5 – 10 Lt (only Red .171, base 8 l + cat. 2 l)		



YachtCoatings

DELTA 3000

TECHNICAL DATA SHEET

Application and use

SURFACE PREPARATION

For surfaces that have been treated with other coatings in bad condition, it is important to remove the previous coat up to the surface.

Steel: Pressure wash with fresh water (200-300 bar) and remove any trace of oil and grease. Perform a sanding treatment of grade Sa 2½ (ISO 8501-1/3). For surfaces covered with shop-primer, perfectly intact and fitted, it is possible to perform a commercial sanding Sa 2 or a mechanical cleaning of degree St 3 (ISO 8501-1/3). The recommended roughness value Rz, obtained after a shot-blasting treatment or a mechanical cleaning, is 50 - 90 µm. Cover the treated metal with DELTA 3000, according to the above mentioned standard, before the appearance oxidation principles or colour variations.

Aluminium, Lead and Alloys: Wash under pressure with fresh water (200-300 bar) and remove all traces of oil and grease. Sandpaper with coarse-grained discs no. P 36 (mechanical cleaning) or, alternatively, carry out the sandblasting treatment, using suitable abrasives: the surface layer of the metal must be completely and uniformly renewed, removing any residual oxidation, and covered with DELTA 3000 on the day of preparation. Be careful not to polish the surface without exceeding it with the engraving; the recommended roughness value of Rz is 50 - 90 µm (ISO 8503).

Wood: The support must be dry, the humidity of the wood must not exceed 18%. All surfaces to be painted must be clean, dry and free of contaminants. Sand with P80-P120 paper. Before applying DELTA 3000, blow with clean, dry air to remove any residual sanding and dirt.

Composite (fiberglass carbon fibre, etc.): Degrease the surface to be treated with a solvent or suitable detergent. Pressurize with fresh water and remove all traces of oil and grease. All surfaces to be painted must be clean, dry and free of contaminants. Sand with sandpaper no. P180 - P220 and primer the treated surface. Before applying DELTA 3000, blow with clean, dry air to remove any residue of sanding and dirt.











YachtCoatings

DELTA 3000

TECHNICAL DATA SHEET

Application data

Mixing ratio by volume		4:1
Mixing ratio by weight Base (comp. A) 653.--- Hardener (comp. B) 651.000C		88 w/w 12 w/w
Pot-life NB do not use this product when Pot-life time is exceeded		8 hrs at 20 °C
Thinner/Cleaning tools NB: the indicated dilution % is considered on the catalyzed product		693 - Roller/Brush (10% max) 693 – Conventional spray/Airless: (10% max)
Application methods		Airless Pressure 150 bar Nozzle 0.3 – 0.6 mm Angular range: 65° - 80°
		Conventional Pressure 3,5 bar Nozzle 1,7 – 1,9 mm
	 	
Dry film thickness per coat	Standard application range	50 – 130 µm
	Recommended	70 µm
Wey film thickness per coat	Standard application range	100 – 260 µm
	Recommended	150 µm
Theoretical coverage	70 µm	7 m ² /l
Practical coverage [loss value 30%]	70 µm	5 m ² /l
Recommended primers	Directly on sandblasted or grinded substrates or two-component paints	





YachtCoatings

DELTA 3000

TECHNICAL DATA SHEET

Notes This product is provided in two tins to be mixed entirely and carefully before use. In case it is required, dilution has to be performed after the mixing of the two components. The physical data of two-component products refer to components that have been already mixed.

Drying time

Temperature °C			10		15		20		30	
			Min	Max	Min	Max	Min	Max	Min	Max
Coverage	Epoxy products or polyesters		12 h	3 days	8 h	3 days	6 h	3 days	4 h	2 days
Sanding			36 h		24 h		18 h		12 h	
Full curing			10 days		7 days		7 days		5 days	

N.B. *The drying times and the overcoating intervals increase with higher thickness of the applied film. Always check that the existing painting film is perfectly dry before applying a further product coat.*

CONDITIONS DURING APPLICATION

In order to avoid the formation of condensation, the surface temperature should be at least 3 °C above dew point. During application and curing, the min. ambient temperature must not be lower than 10 °C or higher than 30 °C and substrate temperature must not be lower than 5 °C, since curing is remarkably reduced at lower temperatures. Application is not advisable when relative humidity exceeds 80%. The term-hygrometric survey should be carried out near the surface to be coated. Make sure there is enough ventilation when the application takes place in closed areas.



YachtCoatings

DELTA 3000

TECHNICAL DATA SHEET

Storage

It is recommended to avoid exposure to air and extreme temperatures. To maximize the shelf life in the can, it is worth checking that the container is well closed during the storage and the temperature is between 10 °C and 35 °C. Avoid exposure to direct sunlight.

Safety rules

Observe the provisions of DPR 303 and 547. Avoid contact with the skin, for example. Operate in well ventilated places and, if in closed areas, use vacuum cleaners, fans and air conveyors. During the application use appropriate protections (masks, gloves, glasses, etc.). Before using, read sections 7-8 of the SDS.

INSTRUCTIONS FOR THE DISPOSAL OF PRODUCTS AND PACKAGING

Empty packaging that contained products: Dispose of empty packaging according to the requirements of the waste disposal law, for example by taking them to the recycling center.

Packages containing the unused products: Dispose of the unused product in accordance with the law of disposal of such waste, for example by taking it to a recycling center, recycling of packaging is prohibited in this case. Do not empty into drains or watercourses. Product packaging must be kept indoor, and the temperature in the storage place must be between 10 °C and 35 °C. Do not expose to sunlight.

Notes

The values indicated in the present technical sheet can have slight variations from one batch to another. All data refer to the mixed product. The applied product must not come in contact with water, chemicals or subjected to mechanical stress before the curing is complete. The wet film thicknesses refer to the undiluted product. With dilution, this value will rise. The above information is the result of accurate laboratory tests and practical experience; however, since the product is predominantly used outside the manufacturer's control, Boero Bartolomeo S.p.A. can only guarantee its quality. The information contained in this sheet may be subject to revision by the Company. For clarification, updates or further information, it is recommended to contact Boero Bartolomeo S.p.A. directly. The present datasheet annuls and replaces every other precedent to this one.

Rev. March 2019

5