



YachtCoatings

ALTURA UV

TECHNICAL DATA SHEET

Product description

<https://www.verfschilderen.nl/altura-uv-gloss.html>

Altura UV is a transparent varnish, with particular brilliance, elasticity and filling power. It is provided with exceptional resistance to marine weather conditions and offers a high-level resistance to UV solar radiation. Easy to apply, it maintains over time its flexibility and its brilliance. It constitutes an exceptional finish for all type of wooden surfaces exposed to interior and external.

Product information

Finish	Shiny		
Colour	Colourless. 000		
Solids (by volume)	ASTM D2369		55 ± 2%
Specific gravity	UNI EN ISO 2811-1		0,92 ÷ 0,96 g/cm ³
Flash Point	UNI EN ISO 13736		30 °C
VOC (calculated average content)	ISO 11890-2/2006		362 g/l
Packaging	0,375 – 0,75 Lt		



YachtCoatings

ALTURA UV

TECHNICAL DATA SHEET

Application and use





SURFACE PREPARATION

New wood or renewed: the support must be perfectly dry, the humidity of the wood must not be over 18%. All the surfaces to paint must be clean dry and free from any trace of contaminants. Sand down with P80-P120 sanding paper. Before proceeding with the application of the provided products, blow using dry and clean air, in order to remove every trace of sanding and dirt. Apply the first coats of ALTURA UV diluted 10 - 15%. Proceed with the following coats (3-5 coats) as well as explained.

Painted wood : sandpaper in order to eliminate every varnish trace during the stripping vessel phase; apply the first coats of ALTURA UV, diluted 5% than proceed with the following coats (2-4 coats) as before.

N.B: Between the coats, use abrasive Scotch Brite fine (grey).

Application data

Thinner/Cleaning tools		703 - Roller/Brush 703 – Conventional spray
Application method		Conventional Pressure 3,5 bar Nozzle 1,2 – 1,4 mm
	 	
Dry film thickness	Standard range application	20 – 40 µm
	Recommended	30 µm
Wet film thickness	Standard range application	40 – 70 µm
	Recommended	55 µm






YachtCoatings

ALTURA UV

TECHNICAL DATA SHEET

Theoretical coverage	30 µm	18 m ² /l
Recommended Primers	Biowood – Polywood	

Drying time

Temperature °C		10		15		20		30	
		Min	Max	Min	Max	Min	Max	Min	Max
Coverage				48 h	7 days	24 h	7days	18 h	7days
Sanding				72 h		48 h		36 h	
Fully cured				7 days		7 days		7 days	

N.B. The drying times and the overcoating intervals increase with higher thickness of the applied film.
Always check that the existing painting film is perfectly dry before applying a further product coat.

CONDITIONS DURING APPLICATION

In order to avoid the formation of condensation, the temperature of the surface should be at least 3 °C above dew point. During the application and curing the min. ambient temperature must not be lower than 15 °C or higher than 30 °C, and the minimum temperature of the support must not be lower than 10°C, because the crosslinking is significantly slowed at temperatures below. Application is not advisable when relative humidity exceeds 80%. The term-hygrometric survey should be carried out near the surface to be coated. Make sure there is enough ventilation when the application takes place in closed areas.



YachtCoatings

ALTURA UV

TECHNICAL DATA SHEET

Storage

It is recommended to avoid exposure to air and extreme temperatures. To maximize the shelf life in the can, it is good to check that the container is well closed during the storage and the temperature is between 10 °C and 35 °C. Avoid exposure to direct sunlight.

Safety rule

Observe the provisions of DPR 303 and 547. Avoid contact with the skin, for example. Operate in well ventilated places and, if in closed areas, use vacuum cleaners, fans and air conveyors. During application, use appropriate protections (masks, gloves, glasses, etc.). Before using, read sections 7-8 of the SDS.

INSTRUCTIONS FOR THE DISPOSAL OF PRODUCTS AND PACKAGING

Empty packaging that contained products: Dispose of empty packaging according to the requirements of the waste disposal law, for example by taking them to the recycling center.

Packages containing the unused products: Dispose of the unused products in accordance with the law of disposal of such waste, for example by taking it to a recycling center, recycling of packaging is prohibited in this case. Do not empty into drains or watercourses. Product packaging must be kept indoor, and the temperature in the storage place must be between 10° C and 35° C. Do not expose to sunlight.



YachtCoatings

ALTURA UV

TECHNICAL DATA SHEET

Note

The values indicated in the present technical sheet can have slight variations from one batch to another. The applied product must not come in contact with water, chemicals or subjected to mechanical stress before the curing is complete. The wet film thickness is referring to the undiluted product. In case of dilution, this value increases. The above information is the result of accurate laboratory tests and practical experience, however, since the product is predominantly used outside the manufacturer's control, Boero Bartolomeo S.p.A. can only guarantee their quality. The information contained in this sheet may be subject to revision by the Company. For clarification, updates or further information, it is recommended to contact Boero Bartolomeo S.p.A. directly. The present datasheet annuls and replaces every other precedent to this one.