

Alkyd Finish

<https://www.verfschilderen.nl/interlac-665.html>

PRODUCT DESCRIPTION A one pack alkyd gloss finish.

INTENDED USES For use as an easily maintained cosmetic finish coat on areas above the waterline.
For use at Newbuilding, Maintenance & Repair or On Board Maintenance.

PRODUCT INFORMATION

Colour CLB000-White, CLD260-Intl. Orange, CLK724-Storm Grey, CLL274-Red, CLL549-Signal Green, CLY999-Black ; and a wide range of colours.

Finish/Sheen High Gloss

Part B (Curing Agent) Not applicable

Volume Solids 48% ±3% (ISO 3233:1998)

Typical Film Thickness 40 microns dry (83 microns wet)

Theoretical Coverage 12 m²/litre at 40 microns dft, allow appropriate loss factors

Method of Application Airless Spray, Brush, Conventional Spray, Roller

Flash Point (Typical) Single Pack 40°C (Product produced and supplied in North America has a flashpoint of 41°C due to locally sourced solvents. There is no detrimental effect on product performance.)

Drying Information	Substrate Temperature			
	5°C	10°C	25°C	35°C
Touch Dry [ISO 9117/3:2010]	18 hrs	14 hrs	6 hrs	5 hrs
Hard Dry [ISO 9117-1:2009]	62 hrs	48 hrs	24 hrs	12 hrs

Overcoating Data - see limitations	Substrate Temperature							
	5°C		10°C		25°C		35°C	
Overcoated By	Min	Max	Min	Max	Min	Max	Min	Max
Interlac 665	36 hrs	ext	24 hrs	ext	24 hrs	ext	16 hrs	ext

REGULATORY DATA

VOC 420 g/lit as supplied (EPA Method 24)
364 g/kg of liquid paint as supplied. EU Solvent Emissions Directive (Council Directive 1999/13/EC)
407 g/lit Chinese National Standard GB23985

Note: VOC values are typical and are provided for guidance purposes only. These may be subject to variation depending on factors such as differences in colour and normal manufacturing tolerances.

Alkyd Finish

CERTIFICATION

When used as part of an approved scheme, this material has the following certification:

- Fire Resistance - Surface Spread of Flame (Exova Warringtonfire)
- Fire Resistance - Surface Spread of Flame (Korean Register of Shipping)
- Fire Resistance - Smoke & Toxicity (Exova Warringtonfire)
- Fire Resistance - Marine Equipment Directive compliant
- Food Contact - Carriage of Grain (NOHA)
- Meets Petrobras Standard N-2492 - Alkyd Finish Gloss

Consult your International Paint representative for details.

SYSTEMS AND COMPATIBILITY

Interlac 665 should only be applied over recommended anticorrosive primers. The primer to be used will depend upon vessel area, existing coatings, coating condition and application location. Typical primers include:

Interprime 198
Intertuf 203
Interprime 128 (in Europe)
Interprime 222 (in South America)
Interprime 234 (in North America)
Interprime 538 (in Europe)
Interlac 497 (applied as a sympathetically coloured undercoat over Interprime 198)

In the Americas, Interlac 665 may also be applied over epoxy primers or epoxy tie coats. Consult International Paint.

Consult your International Paint representative for the system best suited for the surfaces to be protected.

SURFACE PREPARATIONS

Use in accordance with the standard Worldwide Marine Specifications.

All surfaces to be coated should be clean, dry and free from contamination.

High pressure fresh water wash or fresh water wash, as appropriate, and remove all oil or grease, soluble contaminants and other foreign matter in accordance with SSPC-SP1 solvent cleaning.

NEWBUILDING/MAJOR REFURBISHMENT

Interlac 665 should always be applied over a recommended primer coating scheme. The primer surface should be dry and free from all contamination, and Interlac 665 must be applied within the overcoating intervals specified (consult the relevant product data sheet). Areas of breakdown, damage etc., should be prepared to the specified standard (e.g. Sa2½ (ISO 8501-1:2007) and primed prior to the application of Interlac 665

REPAIR

Repair corroded areas with an appropriate International Paint primer (consult the primer data sheet).

OBM

Interlac 665 should always be applied over a recommended primer coating scheme. The primer surface should be dry and free from all contamination, and Interlac 665 must be applied within the overcoating intervals specified (consult the relevant product data sheet). Areas of breakdown, damage etc., should be prepared to the specified standard (e.g. Sa2½ (ISO 8501-1:2007) and primed prior to the application of Interlac 665

Interlac 665 may be applied directly over aged Interlac 665 following thorough fresh water washing and degreasing provided the coating to be overcoated is in an intact and tightly adherent condition. Loose or flaking coatings should be removed back to a firm edge and Interlac 665 or an appropriate primer should be used to repair the area before application of the full coat.

Consult your International Paint representative for specific recommendations.

NOTE

**For use in Marine situations in North America, the following surface preparation standards can be used:
SSPC-SP10 in place of Sa2½ (ISO 8501-1:2007)**

Alkyd Finish

APPLICATION

Mixing	This material is a one pack coating and should always be mixed thoroughly with a power agitator before application.
Thinner	International GTA004. Thinning is not normally required. Consult the local representative for advice during application in extreme conditions. Do not thin more than allowed by local environmental legislation.
Airless Spray	Recommended Tip Range 0.33-0.48 mm (13-19 thou) Total output fluid pressure at spray tip not less than 141 kg/cm ² (2010 p.s.i.)
Conventional Spray	Use suitable proprietary equipment. Thinning may be required.
Brush	Suitable.
Roller	Suitable.
Cleaner	International GTA004
Work Stoppages and Cleanup	Thoroughly flush all equipment with International GTA004. All unused material should be stored in tightly closed containers. Partially filled containers may show surface skinning and/or a viscosity increase of the material after storage. Material should be filtered prior to use.
Welding	In the event welding or flame cutting is performed on metal coated with this product, dust and fumes will be emitted which will require the use of appropriate personal protective equipment and adequate local exhaust ventilation. In North America do so in accordance with instruction in ANSI/ASC Z49.1 "Safety in Welding and Cutting."

SAFETY

All work involving the application and use of this product should be performed in compliance with all relevant national Health, Safety & Environmental standards and regulations.

Prior to use, obtain, consult and follow the Material Safety Data Sheet for this product concerning health and safety information. Read and follow all precautionary notices on the Material Safety Data Sheet and container labels. If you do not fully understand these warnings and instructions or if you can not strictly comply with them, do not use this product. Proper ventilation and protective measures must be provided during application and drying to keep solvent vapour concentrations within safe limits and to protect against toxic or oxygen deficient hazards. Take precautions to avoid skin and eye contact (ie. gloves, goggles, face masks, barrier creams etc.) Actual safety measures are dependant on application methods and work environment.

EMERGENCY CONTACT NUMBERS:

USA/Canada - Medical Advisory Number 1-800-854-6813

Europe - Contact (44) 191 4696111. For advice to Doctors & Hospitals only contact (44) 207 6359191

China – Contact (86) 532 83889090

R.O.W. - Contact Regional Office

Alkyd Finish

LIMITATIONS

Interlac 665 is not suitable for use on immersed areas.

Overcoating information is given for guidance only and is subject to regional variation depending upon local climate and environmental conditions. Consult your local International Paint representative for specific recommendations. Apply in good weather. Temperature of the surface to be coated must be at least 3°C above the dew point. For optimum application properties bring the material to 21-27°C, unless specifically instructed otherwise, prior to mixing and application. Unmixed material (in closed containers) should be maintained in protected storage in accordance with information given in the STORAGE Section of this data sheet. Technical and application data herein is for the purpose of establishing a general guideline of the coating application procedures. Test performance results were obtained in a controlled laboratory environment and International Paint makes no claim that the exhibited published test results, or any other tests, accurately represent results found in all field environments. As application, environmental and design factors can vary significantly, due care should be exercised in the selection, verification of performance and use of the coating.

In the overcoating data section 'ext' = extended overcoating period. Please refer to our Marine Painting Guide - Definitions and Abbreviations available on our website.

UNIT SIZE	Unit Size	Vol	Pack
	20 lt	20 lt	20 lt
	5 lt	5 lt	5 lt
	5 US gal	5 US gal	5 US gal
	1 US gal	1 US gal	5 US gal

For availability of other unit sizes consult International Paint

UNIT SHIPPING WEIGHT (TYPICAL)	Unit Size	Unit Weight
	1 US gal	10 lb
	20 lt	23.9 Kg
	5 lt	6.01 Kg
	5 US gal	49.5 lb

STORAGE	Shelf Life
	24 months minimum at 25°C. Subject to reinspection thereafter. Store in dry, shaded conditions away from sources of heat and ignition

WORLDWIDE AVAILABILITY Consult International Paint.

IMPORTANT NOTE

The information in this data sheet is not intended to be exhaustive; any person using the product for any purpose other than that specifically recommended in this data sheet without first obtaining written confirmation from us as to the suitability of the product for the intended purpose does so at their own risk. All advice given or statements made about the product (whether in this data sheet or otherwise) is correct to the best of our knowledge but we have no control over the quality or the condition of the substrate or the many factors affecting the use and application of the product. Therefore, unless we specifically agree in writing to do so, we do not accept any liability at all for the performance of the product or for (subject to the maximum extent permitted by law) any loss or damage arising out of the use of the product. We hereby disclaim any warranties or representations, express or implied, by operation of law or otherwise, including, without limitation, any implied warranty of merchantability or fitness for a particular purpose. All products supplied and technical advice given are subject to our Conditions of Sale. You should request a copy of this document and review it carefully. The information contained in this data sheet is liable to modification from time to time in the light of experience and our policy of continuous development. It is the user's responsibility to check with their local representative that this data sheet is current prior to using the product.

This Technical Data Sheet is available on our website at www.international-marine.com or www.international-pc.com, and should be the same as this document. Should there be any discrepancies between this document and the version of the Technical Data Sheet that appears on the website, then the version on the website will take precedence.

All trademarks mentioned in this publication are owned by, or licensed to, the AkzoNobel group of companies.

© AkzoNobel, 2015

www.international-marine.com